



Technical Information

Product Name	:	MoTip Polyester Putty			
Article Number	:	000051	000098	000052	000055
Contents	:	250 gram	500 gram	1.000 gram	2.000 gram
Supplier / Producer	:	MOTIP DUPLI B.V. Wolfraamweg 2 NL-8471 XC WOLVEGA Telephone number +31 561 – 69 44 00 Telefax number +31 561 – 69 44 31			

Product description

High quality, universal 2 component polyester putty to level irregularities in surfaces of steel, aluminium, wood, concrete and polyester.

Product characteristics

Very easy to sand
Elastic
Re-sprayable with all lacquer systems
Resistant to chemicals and weather influences
Excellent adhesion

Physical and Chemical Characteristics

Base Putty	:	Polyester resin
Base Harder	:	Benzoyl peroxide
Density	:	1,92 Kg/dm ³
Harder to be added	:	2,5%
Potlife	:	3 to 5 minutes
Layer thickness to apply	:	Up to 2 centimetres
Sandable after	:	approximately 30 minutes
Re-Sprayable after	:	approximately 1 hour
Heat resistant	:	To 120°C

Usage

Before use, carefully read the directions on the packaging and act accordingly.

Processing temperature 15 – 25°C.

Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

Treatment

The surface should be clean, dry and free of grease. Mix the required amount of putty with the harder. Apply in the desired layer thickness. After hardening, sand and when desired apply a fine putty.

The drying time depends on the ambient temperature.

After use, directly clean the tools used.

Do not store the surplus material, mixed with harder, in the can.